




9 outer compacted strands, plastic impregnation




9x17 SLR Compacted



9x26 WSR Compacted



9x31 WSR Compacted



9x36 WSR Compacted

	Diameter		Section mm ²	Mass kg/m	Min. breaking load	
	mm	inch			kN	kN
9x17 SLR	16	5/8	135,4	1,20	1960 MPa 219	2160 MPa 239
	18	-	171,7	1,54	277	302
	19	3/4	191,4	1,72	308	336
9x26 WSR	20	-	213,5	1,92	346	375
	22	7/8	255,2	2,31	416	450
	24	-	303,1	2,74	493	534
	25	-	334,1	3,02	545	586
	25,4	-	350,3	3,17	569	611
	26	-	362,7	3,28	592	631
	28	1-1/8	415,6	3,75	677	721
	28,6	-	430,3	3,89	700	746
	30	-	469,9	4,25	763	814
9x31 WSR	32	1-1/4	534,6	4,84	868	926
	34	1-3/8	617,5	5,56	1015	1075
	35	-	652,9	5,88	1104	1155
	36	-	689,2	6,21	1168	1222
	38	1-1/2	763,9	6,90	1290	1362
	40	-	857,6	7,76	1401	1487
	41	-	858,9	7,72	1488	1570
	42	1-5/8	901,4	8,10	1575	1656
	44	1-3/4	1017,1	9,16	1723	1799
	46	-	1142,0	10,31	1870	1945
	48	-	1235,3	11,18	2034	2112
9x36 WSR	50	2	1278,2	11,48	2205	2286
	52	-	1443,4	12,99	2343	2405
	54	2-1/8	1556,6	14,01	2527	2594
	56	-	1674,0	15,07	2716	2789
	58	-	1784,2	16,03	2934	3012
	60	2-3/8	1914,6	17,24	3160	3244
	62	-	2080,0	18,75	3402	3492
	64	2-1/2	2186,4	19,98	3625	3721

Indicative values – Tolerance on diameter: ArcelorMittal design (0; +4%)

Complast 9 must not be used with a swivel

Depending on applications, design can be specifically adapted. Please contact us for further information.