




8 outer strands, plastic impregnation




8x19 SR



8x26 WSR



8x31 WSR Compacted



8x36 SR Compacted

	Diameter		Section mm ²	Mass kg/m	Min. breaking load		
	mm	inch			1960 MPa	2160 MPa	
					kN	kN	
8x19 SR	6,5	-	23,5	0,20	-	41,8	
	7	-	27,3	0,24	-	48,5	
	7,2	-	28,9	0,26	-	51,6	
	8	5/16	35,8	0,32	-	65,6	
	9	-	45,6	0,41	-	83	
	10	-	56,9	0,51	-	104	
	11	7/16	69,9	0,63	-	128	
	12	-	82,0	0,73	-	150	
	13	1/2	95,8	0,86	-	175	
	14	9/16	110,4	0,99	-	202	
	15	-	127,5	1,14	-	233	
	8x26 WSR	16	5/8	140,1	1,26	231	245
		18	-	177,3	1,59	292	310
		19	3/4	197,5	1,77	326	345
		20	-	218,9	1,96	361	382
22		7/8	264,8	2,37	437	463	
23		-	291,2	2,60	481	503	
24		-	317,1	2,83	523	548	
25,4		-	355,2	3,17	586	614	
26		1	372,1	3,32	614	643	
27		-	401,3	3,58	655	685	
28		1-3/8	420,8	3,72	705	737	
29		-	451,4	3,99	756	790	
30		-	483,1	4,27	809	846	
32		1-1/4	549,6	4,86	920	962	
8x31 WSR		34	1-3/8	619,4	5,56	1030	1051
		35	-	669,3	6,09	1091	1114
		36	-	708,1	6,44	1161	1186
	38	1-1/2	789,0	7,18	1294	1321	
	40	-	874,2	7,96	1434	1464	
	41,3	-	932,0	8,48	1529	1561	
	42	1-5/8	960,2	8,74	1578	1611	
	44	1-3/4	1053,8	9,60	1728	1765	
	44,5	-	1077,9	9,82	1768	1805	
	46	-	1151,8	10,49	1889	1929	
	48	1-7/8	1254,1	11,42	2057	2100	
	50	2	1342,3	12,15	2223	2269	
	51	-	1396,5	12,64	2303	2351	
	52	-	1451,8	13,14	2394	2444	
	8x36 SR	54	2-1/8	1565,6	14,17	2582	-
56		-	1683,7	15,24	2776	-	
58		2-1/4	1806,2	16,35	2978	-	
60		2-3/8	1946,1	17,72	3192	-	
62		-	2078,0	18,92	3408	-	
64		-	2214,3	20,16	3632	-	
65		-	2284,0	20,80	3746	-	

Indicative values – Tolerance on diameter: ArcelorMittal design (0; +4%)

HP8P must not be used with a swivel