

Surface lifts
Skilifte
Telesquíes


Fixes
T- bars
Fixgeklemmt
Fijos

Ame centrale textile ou compacte,
Câblage Lang préformé – Acier clair ou galvanisé.


Synthetic PP or solid plastic core,
Lang lay preformed – Bright or galvanized steel.

Faser- oder Plastikkompakteinlage,
Gleichschlag vorgeformt – Blank oder verzinkt.


Alma central textil o compacta,
Cableado Lang preformado – Acero claro o galvanizado.



6x17 SL
6x(1+8+8)



6x19 SL
6x(1+9+9)



6x26 WS
6x1+5+5.5+10

Diamètre Diameter Durchmesser Diámetro		Masse Mass Gewicht Masa		Section Met. area Querschnitt Sección	Diamètre fils externes Wire diameter Draht Durchmesser Diámetros hilos externos			Force de rupture minimale Minimum breaking load Mindestbruchkraft Fuerza de rotura mínima						Force de rupture totalisée Aggregate breaking load Rechnerische Bruchkraft Fuerza de rotura totalizada					
mm	inch	kg/100m	lb/100ft	mm ²	mm	mm	mm	kN	2000 lbs	kN	2000 lbs	kN	2000 lbs	kN	2000 lbs	kN	kN	kN	kN
					6x17SL	6x19SL	6x26WS	1570 MPa		1770 MPa		1960 MPa		2160 MPa		1570	1770	1960	2160
20	-	141	95	158	1.74	-	-	220	24.8	248	27.9	274	30.8	302	34.0	249	280	310	342
22	-	170	114	192	1.91	1.76	1.63	266	30.0	300	33.8	332	37.3	366	41.1	301	339	376	414
24	-	203	136	228	2.09	1.92	1.78	317	35.6	358	40.2	395	44.4	435	48.9	358	404	447	493
26	1	238	160	268	2.26	2.08	1.92	372	41.8	420	47.2	464	52.1	511	57.4	420	474	525	578
28	-	276	185	310	2.44	2.24	2.07	432	48.5	487	54.7	538	60.4	593	66.6	487	550	609	671
30	-	317	213	356	2.61	2.40	2.22	496	55.7	559	62.8	617	69.4	680	76.5	560	631	699	770
32	1.1/4	360	242	406	2.78	2.56	2.37	564	63.4	636	71.4	702	78.9	774	87.0	637	718	795	876

Valeurs indicatives, Approximate values, Richtwerte, Valores indicativos
To convert rope MBL in kN to tons (2000 lbs) multiply by 0.1124

Nous consulter pour plus d'informations.

Please contact us for further information.

Kontaktieren Sie uns für weitere Informationen.

Para más información, consúltenos.

