

Technical data sheet Undulated steel fibres

Tabix+ 1/60

Dimensions		
Wire diameter (d)	1.00 mm (± 0.04 mm)	
Fibre length (L)	60.0 mm (+2/-3 mm)	
Wave depth (w)	0.40 – 0.65 mm	
Wave length (I)	8.00 mm	
Aspect ratio (L/d)	60	
Number of fibres per kg	2500	
Total fibre length per 10 kg	1550 m	

Recyclable cardboard boxes Net weight/box Boxes/palette 60 Weight/palette 1500 kg The fibres are oriented in one direction Palettes are wrapped or welded in a plastic folio Available also in big bag of 500 kg


Miscellaneous

The described fibre is in accordance with the following standards:

- EN 14889-1 type 1 (cold-drawn wire),
- ASTM A820/A820M-04 type 1 (cold-drawn wire).

Material characteristics

 Tensile strength of drawn wire 1500 N/mm²



All information in this promotional material illustrates products and services in a non final way and invites further technical or commercial explanation. This is not contractual. Copyright ArcelorMittal – June 2011.

ArcelorMittal Bissen & Bettembourg Route de Finsterthal - PO Box 16 L-7703 Bissen T +352 83 57 72 1 F +352 83 56 98





